

AQUACER 497

Paraffin-based wax emulsion for aqueous coatings, printing inks as well as paper coatings for improving water repellency and surface slip.

Product data

Composition

Non-ionic emulsion based on a paraffin wax

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

pH value:	6.5
Non-volatile matter:	50 %
Carrier:	water
Melting point (wax content):	60 °C
Viscosity (23 °C):	< 50 mPa·s
Delivery form:	emulsion

Storage and transportation

Product shelf life in unopened original packaging: 15 months

Temperature sensitive. To be stored and transported between 5 °C and 35 °C. Stir before use.

Applications

Coatings industry

Special features and benefits

AQUACER 497 improves the water repellency and the anti-blocking in aqueous coatings. The additive increases surface slip and at the same time has no significant influence on the gloss of the system.

Recommended use

Architectural coatings	☒
Wood and furniture coatings	☐

☒ Especially recommended ☐ Recommended

Recommended levels

1-3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

The additive should preferably be added to the coating at the end of the production process using a low shear rate. Mix well before use.

Printing inks

Special features and benefits

The additive improves water repellency and anti-blocking in aqueous coatings; it also increases surface slip.

Recommended levels

2-5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

The additive should preferably be added to the coating at the end of the production process using a low shear rate. Mix well before use.

Paper coatings

Special features and benefits

AQUACER 497 provides good resistance to liquids and water vapour in functional barrier coatings. In addition, it can also offer an improvement in the grease resistance of coatings.

Recommended levels

5-30 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

The additive should preferably be mixed well before use to avoid any inhomogeneity. AQUACER 497 should be added using a low shear rate and preferably before incorporating surface-active substances.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
info@byk.com
www.byk.com



Download
our app:
byk.com/app

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK®-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.