

AQUAMAT 272 N

水系塗料、印刷インキおよびオーバープリントワニスの表面特性を向上させる変性PEベースのつや消しワックスディスパージョン

製品データ

組成

変性ポリエチレンワックスディスパージョン

一般性状

本データシートに記載されております数値は代表値であり、品質規格ではございません。

不揮発分 (60 分, 125 °C):	55 %
キャリア:	水
融点 (ワックス分):	125 °C
粒子径 (ヘグマン):	30 µm
粘度 (23 °C, D=800/s):	< 500 mPa·s
pH:	4

食品接触用途

最新の食品接触用途に関する法的適合状況についてはお問い合わせ下さい。
または、www.byk.comにてご確認下さい。

貯蔵および輸送

温度の影響を受けやすいので、5°Cから35°Cの温度で保管および輸送して下さい。
十分に攪拌してから使用して下さい。

特記事項

容器を開放すると、容器内壁の添加剤が完全に乾燥することがあります。乾燥した添加剤の残渣は最終製品の欠陥の原因になりますので、添加剤は均一化し、フィルター処理をしてから使用して下さい。

適用分野

塗料

特長

本添加剤により表面の保護性が向上し、つや消し効果が付与されます。

推奨用途

建築塗料	■
木工および家具用塗料	■
工業用塗料	■
皮革仕上げ	□

■ 最適 □ 適

推奨添加量

つや消しの度合いにより、全配合に対して添加剤として 1-6%

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

添加方法

本添加剤は低せん断力で製造工程の最後に塗料に添加して下さい。十分に攪拌してから使用して下さい。

印刷インキおよびオーバープリントワニス

特長

本添加剤により耐摩耗性が向上し、つや消し効果が付与されます。

推奨添加量

全配合に対して添加剤として1-2%

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

添加方法

本添加剤は低せん断力で製造工程の最後に塗料に添加して下さい。十分に攪拌してから使用して下さい。

ビックケミー・ジャパン株式会社

本 社: 東京都新宿区市谷本村町3-29

大 阪: 大阪市北区堂島浜1-4-4

<http://www.byk.com/jp>



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSORB®, RECYCLOSTAB®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany