

BYK-1796

Silicone-containing defoamer for solvent-borne, high-solid, and solvent-free applications. Particularly suitable for 100 % 2-component systems. Extremely high defoaming action.

Product data

Composition

Blend of polyether-modified polysiloxanes with hydrophobic particles

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.00 g/ml

Active substance: 100 %

Flash point: > 100 °C

Storage and transportation

Mix well before use.

Applications

Coatings industry

Special features and benefits

BYK-1796 is an outstanding silicone defoamer that is especially suitable for 100 % 2-component systems. The additive displays very good defoaming and is effective against both macro and microfoam. Even in low doses, BYK-1796 has very powerful defoaming properties, which makes it particularly recommended for highly viscous systems that have a certain tendency towards foam stabilization. Furthermore, the additive is characterized by being very effective in high-solid and solvent-free systems based on epoxy and polyurethane resins, as they are used in floor coatings or protective coatings.

Recommended use

Floor coatings	<input checked="" type="checkbox"/>
Protective coatings	<input type="checkbox"/>
Wood and furniture coatings	<input type="checkbox"/>
General industrial coatings	<input type="checkbox"/>
Architectural coatings	<input type="checkbox"/>

especially recommended recommended

Recommended levels

0.1–1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

To achieve optimal defoaming, BYK-1796 should be added as early as the millbase stage. If incorporating at a later stage, sufficiently high shear forces must be applied to ensure a good distribution of the defoamer and to prevent cratering.

Special note

Due to the strong defoaming power of BYK-1796, it is therefore recommended to check the intercoat adhesion and recoatability when it is used in multi-layer systems.

Adhesives and sealants**Special features and benefits**

BYK-1796 is a silicone defoamer for 100 % 2-component epoxy and polyurethane systems. The additive displays very efficient defoaming of both macro and microfoam. Even in low doses, BYK-1796 has very powerful defoaming properties. The additive is therefore particularly recommended for highly viscous systems that have a certain tendency towards foam stabilization.

Recommended use

Epoxy adhesives	<input checked="" type="checkbox"/>
Polyurethane adhesives	<input type="checkbox"/>

especially recommended recommended

Recommended levels

0.1–1.5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

Stir in the resin before adding other components.

Thermosets**Special features and benefits**

BYK-1796 displays an outstanding efficiency when releasing air from all epoxy resin systems such as cast resins, infusion or winding systems. Furthermore, it has very good degassing properties in polyurethane systems, like, for example, transparent gel coats. The use of BYK-1796 shortens the evacuation time in the production process or the degassing times in the application, and it produces a more high-quality product.

Recommended use

Epoxy resins	<input checked="" type="checkbox"/>
Polyurethane resins	<input checked="" type="checkbox"/>

especially recommendedn recommended

Recommended levels

0.1–1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

To achieve an optimum degassing, BYK-1796 should be added to the epoxy resin already at the start of the production. If incorporating at a later stage, sufficiently high shear forces must be applied to ensure a good distribution of the air release agent, and to prevent surface defects.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.