

BYK-1852

Silicone- and aromatic-free, polymer-based defoamer for solvent-borne and solvent-free systems.

Product data

Composition

Solution of polyolefins

Aromatic-free
Silicone-free

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.77 g/ml
Non-volatile matter (10 min, 150 °C):	20 %
Solvents:	dearomatized hydrocarbons
Flash point:	42 °C

Storage and transportation

To be stored and transported between 0 °C and 50 °C.

Special note

BYK-1852 is the replacement product for BYK-052 N and an alternative to BYK-053 N.

Applications

Coatings industry

Special features and benefits

BYK-1852 is an excellent silicone-free defoamer for a range of solvent-borne and solvent-free coating systems. It is a powerful and very effective defoamer with good compatibility that is especially suitable for medium to non-polar systems and does not reduce the intercoat adhesion when recoating.

Recommended use

General industrial coatings	<input checked="" type="checkbox"/>
Automotive coatings	<input type="checkbox"/>
Architectural coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>
Marine and protective coatings	<input checked="" type="checkbox"/>
Floor coatings	<input checked="" type="checkbox"/>

besonders empfohlen empfohlen

Recommended levels

0.05–0.5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

To achieve optimal defoaming, the defoamer should be added as early as the millbase stage. If incorporating at a later stage, sufficiently high shear forces must be applied to ensure a good distribution and to prevent cratering.

Special note

In clearcoats, the effect on transparency must be tested.

Printing inks**Special features and benefits**

BYK-1852 prevents foam formation in solvent-borne printing ink systems during production and filling. It prevents air entrapment during processing. The additive displays a spontaneous foam-destroying effect and does not reduce the intercoat adhesion when recoating.

Recommended use

Printing inks	■
Overprint varnishes	■

■ besonders empfohlen □ empfohlen

Recommended levels

0.05–0.5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

To achieve optimal defoaming, the defoamer should be added as early as the millbase stage. If incorporating at a later stage, sufficiently high shear forces must be applied to ensure a good distribution and to prevent cratering.



Your local
contact

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.