

BYK-1880

Solvent-free, silicone-containing defoamer for airless or air-assisted airless application of solvent-borne and solvent-free systems. Especially effective against application-related microfoam. Not available in Japan.

Product data

Composition

Polyether-modified polysiloxanes

SVHC label-free (EU SDS)

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 0.99 g/cm³

Active substance: 100 %

Flash point: 93 °C

Delivery form: liquid

Storage and transportation

Product shelf life in unopened original packaging: 36 months

To be stored and transported at a temperature below 50 °C. Separation or turbidity may occur. Stir before use.

Special note

The cyclic siloxane content D4/D5/D6 of BYK-1880 is less than 0.1% in each case, therefore the SVHC label is not required in the safety data sheet.

Applications

Coatings industry

Special features and benefits

BYK-1880 is a highly effective, solvent-free, and silicone-containing defoamer. The additive has been especially designed for 2-pack high-solid PUR systems that are difficult to defoam and are applied by airless or air-assisted airless spray. Furthermore, the product can also be used in conventional spray-applied systems and is widely applicable in many solvent-borne and solvent-free coatings (e.g. alkyds and 2-pack epoxy systems). The additive exhibits strong defoaming even in higher film thicknesses and is particularly effective against microfoam. The defoamer is also excellent against macrofoam. BYK-1880 shows no negative influence on film properties such as gloss, leveling, or adhesion.

Recommended use

General industrial coatings	<input checked="" type="checkbox"/>
Marine and protective coatings	<input checked="" type="checkbox"/>
Automotive refinish coatings	<input type="checkbox"/>
Floor coatings	<input type="checkbox"/>

especially recommended recommended

Recommended levels

0.3–1.0 % additive (as supplied) based on the total formulation, in exceptional cases up to 1.5 %.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

For best effectiveness, the defoamer should be incorporated into the letdown of the formulation. For sensitive systems, which tend to have surface defects, 2/3 of the amount should be added to the millbase and 1/3 to the letdown.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
info@byk.com
www.byk.com



Download
our app:
byk.com/app

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.