

BYK-390

Surface additive on polyacrylate basis for solvent-borne systems. Prevents boiling marks in baking systems and has an air-releasing effect.

Product data

Composition

Solution of a polyacrylate

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.90 g/cm ³
Non-volatile matter (60 min, 105 °C):	50 %
Solvent:	xylene
Flash point:	27 °C
Color:	light yellow
Delivery form:	liquid

Storage and transportation

Product shelf life in unopened original packaging: 60 months
 To be stored and transported at a temperature below 40 °C.

Applications

Coatings industry

Recommended use

Automotive OEM coatings	<input checked="" type="checkbox"/>
-------------------------	-------------------------------------

especially recommended recommended

Recommended levels

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Special note

It is recommended to pre-dilute the additive with solvents that contain aromatics.

**Your local
contact****BYK-Chemie GmbH**Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
info@byk.com
www.byk.comDownload
our app:
byk.com/app

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.