

BYK-MAX NU 4232

Granulated nucleation agent to increase the crystallization speed and amount of spherulites in the polymer.

Product Data

Composition

Additive concentrate

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density: 500-650 kg/m³
MFR (230 °C, 2.16 kg): 12 g/10 min
Active substance: 2 %
Supplied as: White to off-white granulate

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Store in sealed containers in a cool, dry, and well-ventilated location.

Applications

Thermoplastics

Special Features and Benefits

BYK-MAX NU 4232 contains a powerful nucleation agent with a very high level of dispersion, offering the optimum balance between increased production speed and improved physical properties. The nucleation agent increases crystallization during cooling, thereby accelerating cooling and at the same time encouraging a consistently crystalline structure. BYK-MAX NU 4232 facilitates high throughput by improving isotropy, which enables the production cycles in processing plants to be reduced. The more homogeneous crystallization prevents defects during molding and increases the dimensional stability, rigidity, and thermal stability, especially when compared with pigmented or other nucleated systems. By using BYK-MAX NU 4232, processed material cools up to 25 % more quickly, which offers a cost-saving potential through increased machine capacity. It also helps achieve a lower extrusion temperature as a result of a more regular polymer flow. When using the product, no sink marks, cavities, or deformation occur after demolding in pigmented/talc-filled systems. There is no need to make color-specific machine adjustments.

Recommended Use

Automotive parts	<input checked="" type="checkbox"/>
Interior vehicle trims	<input checked="" type="checkbox"/>
Boxes	<input checked="" type="checkbox"/>
Housing	<input checked="" type="checkbox"/>
Packaging	<input checked="" type="checkbox"/>
Tanks	<input checked="" type="checkbox"/>
Bottles	<input checked="" type="checkbox"/>
Household products	<input checked="" type="checkbox"/>
Caps and closures	<input checked="" type="checkbox"/>

especially recommended recommended

Recommended Levels

1-3 % additive (as supplied) based upon the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be processed in injection molding, thermoforming, and extrusion blow molding processes.

Special Note

Compared with non-nucleated PP types, the extrusion temperature can be reduced by 20-30 °C and the cooling time by up to 25 %. The ideal process parameters should be determined through testing.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.