

BYK-MAX P 4200

Granulated processing additive for the use in thermoplastic PP compounds to reduce VOC and odour.

Product Data

Composition

Aqueous solution of polymeric, surface-active substances adsorbed onto a polypropylene carrier

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density: 370 kg/m³
MVR of the carrier (230 °C, 2.16 kg, ISO 1133): 2-3 cm³/10 min
Melting point: 160 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Thermoplastics

Special Features and Benefits

The addition of BYK-MAX P 4200 during vacuum degassing reduces or even entirely removes the components of the compound that cause odor and emissions. The additive has no negative influence on the mechanical and optical properties of the mixture. It is simple to handle and no additional investment in machinery is required.

Recommended Use

The additive is particularly recommended for PE-based and PP-based thermoplastic compounds and also for ABS.

Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

BYK-MAX P 4200 should be added to the thermoplastic during or prior to compounding. For optimum performance of the additive, vacuum degassing at a minimum of 100 mbar is recommended. It should preferably be processed using only one degassing vent just before the end of the extruder.

BYK-MAX P 4200

Data Sheet
Issue 09/2019



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOÍSITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITÉ®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany