

BYK-P 9051

低粘度で離型性を有する、BMC/DMC用加工助剤

製品データ

組成

界面活性物質とポリマーの組合せ

一般性状

本データシートに記載されております数値は代表値であり、品質規格ではございません。

酸価:	157 mg KOH/g
比重 (20 °C):	0.97
屈折率 (20 °C):	1.487
不揮発分 (10分, 150°C):	99%
引火点:	> 100 °C

食品接触用途

最新の食品接触用途に関する法的適合状況についてはお問い合わせ下さい。または、www.byk.comにてご確認下さい。

適用分野

BMC, DMC

特長

BYK-P 9051は離型性を有する加工助剤で、BMC/DMCの加工性を向上させます。本添加剤が原因でくもりが生じることはございません。BMC製前照灯反射鏡に使用すると、最終製品のくもりが低減します。本製品は低粘度なので、BYK-P 9050よりも加工性が高いです。BYK-P 9051はBMC/DMCにのみ最適です。噴射パラメータの調整が必要になることがあります。

推奨添加量

樹脂全体に対して添加剤として3-4 %

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

添加方法

攪拌しながら、UP樹脂に添加して下さい。従来の離型剤は配合から除いて下さい。

BYK-P 9051

Data Sheet
Issue 06/2015

ビツケミー・ジャパン株式会社
本社:東京都新宿区市谷本村町3-29
大阪:大阪市北区堂島浜1-4-4
<http://www.byk.com/jp>



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany