BYK-P 9908

貯蔵タンク内でのポリオールブレンドの相分離を防ぐ、ポリウレタン系用加工助剤／相溶化剤。この双親性高分子乳化剤を使用することで、施工現場での作業工程を一段階削減でき、工程の信頼性を高め、施工時間も短縮。

製品データ

組成
アクリレートコポリマーの溶液

一般性状
本データシートに記載された数値は代表値であり、品質規格ではございません。

密度 (20 °C):	1.02 g/ml
屈折率 (20 °C):	1.457

食品接触用途
最新の食品接触用途に関する法的適合状況についてはお問い合わせください。または、下記URLをご参照ください。
www.byk.com

貯蔵および輸送
25℃未満の温度では、分離や濁りが生じる場合があります。使用前に十分に撹拌してください。

適用分野

熱硬化性樹脂

特長
BYK-P 9908は、相分離を起こしやすいポリオールブレンドの相溶性を向上させ、特殊ポリウレタンフォームやCASE用途の製造に使用されます。この添加剤はエマルジョンを安定化させるため、ポリオールブレンドの取り扱いを容易にします。これにより、反応混合物および最終製品の均一性が向上します。取り扱いが容易かつ迅速になることで、加工コストの削減とプロセス制御の向上につながります。また、包装コストやクレーム対応にかかるコストも削減されます。

推奨用途

ポリエステル	■
ポリエーテル	■
PTMEG	■
1,4-ブタンジオール	■

■ 最適

推奨添加量
全配合に対して添加剤と して、1-3%

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

添加方法
本添加剤は、不相溶の成分を添加する前に、ポリオールに添加してください。

Your local contact

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK®-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® **are registered trademarks of the BYK group.**

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.