

## BYK-W 940

Wetting and dispersing additive for mineral fillers in unsaturated resin systems and adhesives. The additive prevents the flooding/floating and settling of pigments and fillers in epoxy and VE/UP-based laminates. Reduction in the flooding/floating of colored pigments in gel coats.

### Product Data

#### Composition

Solution of an unsaturated polycarboxylic acid polymer with a polysiloxane copolymer

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	150 mg KOH/g
Density (20 °C):	0.95 g/ml
Refractive index (20 °C):	1.486
Non-volatile matter (10 min., 150 °C):	50 %
Flash point:	28 °C

#### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

#### Storage and Transportation

Separation or turbidity may occur during storage and transportation. Warm to 30-60 °C and mix well.

### Applications

#### Ambient Curing Systems

#### Special Features and Benefits

BYK-W 940 is a wetting and dispersing additive for mineral fillers as well as inorganic and organic pigments. It stabilizes the solid particles in resin systems and prevents the settling of fillers and the flooding/floating of pigments. BYK-W 940 is primarily used in color pastes and gel coats based on unsaturated polyester resins.

#### Recommended Levels

Amount of additive (as supplied) based upon solids:

Inorganic pigments:	0.5-3 %
Organic pigments:	2.5-5 %
Fillers:	0.5-1.5 %

## BYK-W 940

Data Sheet  
Issue 01/2014

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

For optimum performance, the additive should be added before the solids.

### Adhesives & Sealants

#### Special Features and Benefits

BYK-W 940 is a wetting and dispersing additive for mineral fillers as well as inorganic and organic pigments. It stabilizes the solid particles in adhesive systems and prevents the settling of fillers and the flooding/floating of pigments. BYK-W 940 is recommended for use in epoxy-based and polyester-based adhesive systems. It contains a polysiloxane copolymer to reduce flooding/floating.

#### Recommended Levels

Amount of additive (as supplied) based upon solids:

Inorganic pigments: 0.5-3 %  
Organic pigments: 2.5-5 %  
Fillers: 0.5-1.5 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

For optimum performance, the additive should be added before the solids.

### Pultrusion

#### Special Features and Benefits

BYK-W 940 prevents the settling of pigments and fillers in VE/UP-based formulations for pultrusion applications.

#### Recommended Levels

Amount of additive (as supplied) based upon solids:

Inorganic pigments: 0.5-3 %  
Organic pigments: 2.5-5 %  
Fillers: 0.5-1.5 %

### Incorporation and Processing Instructions

For optimum performance, the additive should be added before the solids.



Additive Guide



BYK-Chemie GmbH  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

info@byk.com  
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKIET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany