

DISPERBYK-2150

Wetting and dispersing additive for solvent-borne coating systems and binder-containing pigment concentrates with broad compatibility. Particularly compatible with thermoplastic acrylates (TPA) and cellulose nitrate.

Product Data

Composition

Solution of a block copolymer with basic, pigment-affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	57 mg KOH/g
Density (20 °C):	1.01 g/ml
Non-volatile matter (10 min., 150 °C):	52 %
Solvents:	Methoxypropylacetate
Flash point:	44 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Separation or turbidity may occur during storage and transportation.
Warm to 30-60 °C and mix well.

Special Note

Before using in white baking enamel coatings, check whether DISPERBYK-2150 causes yellowing. In this case DISPERBYK-180 is recommended to stabilize titanium dioxide.

Applications

Coatings Industry

Special Features and Benefits

The additive defloculates pigments by steric stabilization. It also generates a uniform electrical charge in the pigment particles. The resulting repulsion effect and the steric stabilization prevent any coflocculation which leads to flood and float-free color in pigment blends. As a result of the small particle sizes of the defloculated pigments, high levels of gloss can be achieved and the color strength is improved. In addition, the additive increases transparency in transparent pigments and hiding power in opaque pigments. Viscosity is reduced. In this way, the leveling properties are also improved and higher pigment load is possible.

Recommended Use

DISPERBYK-2150 has excellent compatibility with all standard solvent-borne coating binders, in particular also with thermoplastic acrylates (TPA) and cellulose nitrate. It is particularly recommended for the manufacture of pigment concentrates which contain binders. Since it greatly reduces the mill base viscosity, it enables a high pigment content in the concentrate. The additive can also be used for direct pigment grinding in solvent-borne coatings.

Recommended Levels

Additive dosage as supplied based on pigment:

Inorganic pigments:	10-15 %
Titanium dioxides:	3-5 %
Organic pigments:	30-60 %
Carbon blacks:	60-140 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. Pre-mix the resin and solvent components of the mill base and then gradually let the additive flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany