

PURABYK-R 5511

Rheology additive based on activated phyllosilicate for aqueous systems to generate thixotropic flow behavior in personal care applications (COSMOS APPROVED, NATRUE Approved).



NATRUE Approved

Product data

Composition

Modified activated phyllosilicate
 (INCI: Bentonite or Montmorillonite)

Vegan

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density:	550-750 kg/m ³
pH value (2 % in water):	10.6
Water content:	max. 13 %
Sieve residue (325 Mesh/44 µm):	max. 5 %
Degree of whiteness (Elrepho R 457):	approx. 60-65 %
Color:	off-white
Delivery form:	powder

Storage and transportation

Product shelf life in unopened original packaging: 24 months

Moisture sensitive. Store dry in sealed containers. To be stored and transported between -30 °C and 50 °C.

Applications

Personal care

Special features and benefits

PURABYK-R 5511 generates a thixotropic flow behavior in aqueous systems and provides excellent anti-settling properties. This enables the production of storage-stable formulations and facilitates their application. The additive is purely inorganic and stable against diluted acids and bases. Gels produced with PURABYK-R 5511 are also resistant to oxidation. The additive is compatible with anionic and nonionic surfactants as well as most emulsions and pigments.

Recommended use

Pressed powders	<input checked="" type="checkbox"/>
Blush	<input checked="" type="checkbox"/>
Eye makeup	<input checked="" type="checkbox"/>
Facial masks	<input checked="" type="checkbox"/>
Liquid makeup	<input type="checkbox"/>
Skin cleansing products	<input type="checkbox"/>

especially recommended recommended

Recommended levels

1-10 % additive (as supplied) based on the total formulation, depending on the application.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

PURABYK-R 5511 is hydrophilic and can be easily wetted with water. It already starts to swell in cold water, but the use of warm water facilitates and accelerates the dispersion. To achieve optimum efficiency, complete dispersion of the material is necessary. Therefore, PURABYK-R 5511 should be incorporated under high shear forces, e.g. by using a dissolver.

The additive can be used as pre-manufactured pre-gel (containing 5–10% PURABYK-R 5511). Stirring for approx. 15 minutes under high shear is recommended. To avoid post-thickening effects, this pre-gel should be allowed to age overnight before incorporation into the formulation. The pre-gel is then added to the water slowly whilst slowly stirring.

PURABYK-R 5511 can also be added as a powder to the water phase of the formulation.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
info@byk.com
www.byk.com



Download
our app:
byk.com/app

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.