

RHEOBYK-R 606

Liquid rheology additive for solvent-borne and solvent-free adhesives and sealants based on polyurethane, epoxy, and acrylate resins that contain pyrogenic silica or organophilic phyllosilicates.

Product Data

Composition

Polyhydroxy carboxylic acid ester

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.01 g/ml
Refractive index (20 °C): 1.495
Flash point: > 100 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Adhesives & Sealants

Special Features and Benefits

RHEOBYK-R 606 is a thixotropic-reinforcing additive for polyurethane, epoxy, and acrylate resins that are rendered thixotropic with pyrogenic silica or organophilic phyllosilicates (organoclays). It reinforces the hydrogen bonds of the silica and phyllosilicates, resulting in increased thixotropy. For this reason, it achieves sufficiently high anti-sagging properties, with improved leveling and air release properties even with low quantities of silica or phyllosilicates.

Recommended Levels

5-15 % additive (as supplied) based upon the pyrogenic silica or organophilic phyllosilicates (organoclays).

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added to the resin before incorporating the silica/phyllosilicates whilst stirring. Post-addition is also possible.

RHEOBYK-R 606

Data Sheet
Issue 12/2018



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSORB®, RECYCLOSTAB®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany