

SCONA TPPE 2400 GAHD

Viscosity modifier for polyamide formulations to increase melt strength and processing viscosity in extrusion applications. Compatibilizer for recyclates of polyolefins and polar impurities to improve mechanical and optical properties.

Product data

Composition

Chemically modified high density polyethylene

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Grafting functionality:	acrylic acid
Grafting level:	5 %
MVR (190 °C, 2.16 kg):	11 cm ³ /10 min
Drying loss (180 min, 110 °C):	< 0.5 %
Color:	off-white
Delivery form:	pellet

Storage and transportation

Store in sealed containers in a cool, dry, and well-ventilated location.
To be stored and transported at temperatures below 40 °C.

Applications

Thermoplastics

Special features and benefits

SCONA TPPE 2400 GAHD is a modifier based on a polyethylene (HDPE) functionalized with acrylic acid. Even at very low concentrations, the additive leads to a significant increase in melt strength and processing viscosity in polyamide formulations, especially in extrusion applications. In addition, it provides an increase in impact strength and hydrolysis stability in blends of polyamide and polyethylene. The high and consistent grafting level of SCONA TPPE 2400 GAHD ensures high efficiency and very consistent product performance. As a result, the additive also achieves excellent adhesion to polar surfaces and substrates, such as metals. Furthermore, the additive is an excellent compatibilizer for polar impurities in polyolefin recycling applications. As a dispersing aid, it improves mechanical properties in highly filled polyethylene compounds.

Recommended use

Adhesion promoter	<input type="checkbox"/>
Compatibilizer	<input checked="" type="checkbox"/>
Dispersing aid	<input type="checkbox"/>
Impact modifier	<input type="checkbox"/>
Viscosity modifier	<input checked="" type="checkbox"/>

especially recommended recommended

Recommended levels

1–10 % additive (as supplied) based on the total formulation, depending on desired properties and application.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

Incorporate the product with high shear forces by means of a twin-screw extruder to ensure a proper dispersion in the matrix.

**BYK-Chemie GmbH**

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.