

# SCONA TPPP 2112 FA

Adhesion promoter for TPE-S overmolding compounds and dispersing agent for clays in polypropylene.

## Product Data

### Composition

Polypropylene functionalized with maleic anhydride

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

MFR (190 °C, 2.16 kg): 2-7 g/10 min

Drying loss (3 h, 110 °C): < 0.5 %

MAH content: 0.9-1.2 %

Supplied as: Powder

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Storage temperature max. 35 °C, relative humidity < 80 %. Avoid direct sunlight and contact with water.

### Special Note

The modifier is also available as a granulate under the name SCONA TPPP 2112 GA.

## Applications

### Thermoplastics

#### Special Features and Benefits

In combination with SCONA TSKD products the modifier improves adhesion of TPE-S overmolding compounds on hard substrates (such as PC, PA, ABS). Due to the high grafting level, only part of the PP in the TPE compound must be replaced with the modifier. To disperse clays, it is recommended that the modifier is used in polypropylene, especially also for solid masterbatches.

## Recommended Levels

In overmolding compounds, the amount of additive depends on the PP content of the formulation. To disperse clays, use approx. 100 % of the modifier as supplied based upon the clay content. The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

For TPE adhesion formulations, it is recommended that the adhesion promoter is used in granulate form (SCONA TPPP 2112 GA). For PP/clay compounds, a concentrate made from clay and the modifier is created by means of a twin-screw extruder with high shear forces first, which is then incorporated into the PP.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®  
**are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.