

# SCONA TPPP 9012 GA

長短ガラス繊維強化ポリプロピレン、ガラス繊維コンパウンド用カップリング剤

## 製品データ

### 組成

マレイン酸無水物で機能化させたポリプロピレン

### 一般性状

本データシートに記載されております数値は代表値であり、品質規格ではございません。

MFR (190 °C, 2.16 kg): 50–110 g/10 分

揮発分 (3 h, 110 °C): < 0.5%

MAH含有量: > 0.9%

形状: 粒状

### 食品接触用途

最新の食品接触用途に関する法的適合状況についてはお問い合わせ下さい。または、[www.byk.com](http://www.byk.com)にてご確認下さい。

### 貯蔵および輸送

35°C以下の温度、相対湿度80%未満で保管して下さい。直射日光および水との接触を避けて下さい。

### 特記事項

本添加剤の粉末バージョンがSCONA TPPP 9012 FAIになります。

## 適用分野

### 熱可塑性樹脂

#### 特長

SCONA TPPP 9012 GAは、低添加量でも非常に効果的な長短ガラス繊維強化PPコンパウンド用カップリング剤です。コンパウンドの機械的性質を向上させますが、変色への影響はございません。

#### 推奨用途

長短ガラス繊維強化ポリプロピレンコンパウンド用カップリング剤

#### 推奨添加量

ガラス繊維の含有量により、全配合に対して添加剤として0.5-2%

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

#### 添加方法

ファイバーおよびフィラーへの良好な濡れ性は効果的なコンパウンドを製造するための必須条件です。そのため、本製品は必ず主要投入口で添加して下さい。

#### ビックケミー・ジャパン株式会社

本 社: 東京都新宿区市谷本村町3-29

大 阪: 大阪市北区堂島浜1-4-4

<http://www.byk.com/jp>



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBLYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany