

SCONA TSPPR 31113 GB

Compatibilizer and coupling agent for polypropylene and polypropylene elastomers to improve the mechanical properties and adhesion performance of highly polar materials such as metals, wood, natural fibers, fabrics, and mineral fillers.

Product Data

Composition

Polypropylene elastomer functionalized with maleic acid anhydride

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Grafting functionalization:	Maleic acid anhydride
Degree of grafting:	1.2 %
MVR (170 °C, 1.2 kg):	100 cm ³ /10 min
Drying loss (3h, 110 °C):	< 0.5 %
Supplied as:	Granulate
Color:	Pale yellow

Storage and Transportation

Storage temperature max. 35 °C, relative humidity < 80 %. Avoid direct sunlight and contact with water.

Applications

Thermoplastics

Special Features and Benefits

SCONA TSPPR 31113 GB is a polypropylene elastomer grafted with maleic acid anhydride that makes it possible to achieve a significant improvement in the mechanical properties and/or adhesion performance. The grafting increases the polarity of the plastic, thereby promoting adhesion to highly polar materials such as metals, wood, natural fibers, fabrics, and mineral fillers. It can also act as a compatibilizer, dispersing agent, and coupling agent for polypropylene-elastomer composites and multi-layer systems. Other typical applications include calendered and extruded multi-layer films and profiles.

Recommended Levels

0.5-5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Good wetting of the fibers/fillers is required for effective compounding. For this reason, it is preferable to add the product via the main feed.

SCONA TSPPR 31113 GB

Data Sheet
Issue 09/2021



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFLOUR®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.