

ANTI-TERRA-U 80

Wetting and dispersing additive for solvent-borne systems to stabilize inorganic pigments.

Product Data

Composition

Solution of a salt of unsaturated polyamine amides and low-molecular acidic polyesters

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	30 mg KOH/g
Acid value:	40 mg KOH/g
Density (20 °C):	0.99 g/ml
Non-volatile matter (10 min., 150 °C):	80 %
Solvents:	Butylglycol
Flash point:	66 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Separation or turbidity may occur during storage and transportation. Warm to 30-60 °C (86-140 °F) and mix well.

Special Note

For optimum performance, the additive must be incorporated into the millbase before addition of pigments.

BYK-Chemie GmbH

P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK® and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER® and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions - Printed in Germany