

BYK-1791

Aromatic-free, polymer-based defoamer (silicone-free) for radiation-curing systems (wood and industrial coatings, printing inks and adhesives) that has a spontaneous defoaming effect as well as high transparency and low cratering tendency.

Product Data

Composition

Solution of polyolefin

Free from aromatic
compounds

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.80 g/ml
Non-volatile matter (10 min., 150 °C):	40,5%
Solvents:	Isoparaffins
Flash point:	37 °C

Applications

Coatings and Printing Inks

Special Features and Benefits

BYK-1791 has a spontaneous defoaming effect combined with high transparency and low cratering tendency. It is recommended for solvent-borne and solvent-free systems, particularly for radiation-curing wood and industrial coatings, printing inks and overprint varnishes.

Recommended Levels

0.1-1.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Due to its high incompatibility, the defoamer must be incorporated at high shear forces (in the mill base) to ensure good distribution. Otherwise defects may occur in the system.

Adhesives & Sealants

Special Features and Benefits

BYK-1791 is recommended for the defoaming of solvent-free, radiation-curing (UV and ESH) adhesives.

Recommended Levels

0.1-1.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Due to its high incompatibility, the defoamer must be incorporated at high shear forces (in the mill base) to ensure good distribution. Otherwise defects may occur in the system.



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.