

DISPERBYK-168

Wetting and dispersing additive for solvent-borne and solvent-free radiation-curable coatings, printing inks and adhesives.

Product data

Composition

Solution of modified polyurethane

Aromatic-free

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	1.11 g/cm ³
Non-volatile matter (20 min, 150 °C):	30 %
Solvent:	dicarboxylic acid ester
Flash point:	100 °C
Amine value:	10.5 mg KOH/g
Delivery form:	liquid

Storage and transportation

Product shelf life in unopened original packaging: 60 months

Stir before use. Separation or turbidity may occur at temperatures below 5 °C. In this case, warm to 30-40 °C and stir.

Special note

The treatment of some organic pigments can negatively influence the effectiveness of the additive. In these cases, tests with the untreated pigment of the same type may be successful.

Applications

Coatings industry

Special features and benefits

The additive deflocculates the pigments and stabilizes them by means of steric hindrance. It provides equal electrical charge to the pigment particles. The resulting repulsion and the steric stabilization prevent a possible co-flocculation, which leads to flood and float-free color in pigment mixtures. The deflocculating properties of the additive increase gloss, color strength, transparency, and hiding power and reduce the viscosity of the millbase.

Recommended use

The additive is recommended for radiation-curable industrial coatings, can coatings and coil coatings.

Recommended levels

Amount of additive (as supplied) based on the pigment:

Inorganic pigments:	10-15 %
Titanium dioxide:	5-6 %
Organic pigments:	30-90 %
Carbon black:	70-140 %

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.

Printing inks**Special features and benefits**

The additive deflocculates the pigments and stabilizes them by means of steric hindrance. It provides equal electrical charge to the pigment particles. The resulting repulsion and the steric stabilization prevent a possible co-flocculation, which leads to flood and float-free color in pigment mixtures. The deflocculating properties of the additive increase gloss, color strength, transparency, and hiding power and reduce the viscosity of the millbase.

Recommended use

The additive is particularly recommended for UV-curable flexo and offset printing inks. It increases gloss and transparency. DISPERBYK-168 reduces the dispersion time, lowers viscosity and increases color strength.

Recommended levels

Amount of additive (as supplied) based on the pigment:

Titanium dioxide:	2.5-5 %
Organic pigments:	10-20 %
Carbon black:	10-20 %

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.

Adhesives and sealants**Special features and benefits**

The additive deflocculates the pigments and stabilizes them by means of steric hindrance, which leads to a reduction in viscosity and higher transparency. DISPERBYK-168 reduces the dispersion time.

Recommended use

DISPERBYK-168 is recommended for stabilizing titanium dioxide, organic pigments and carbon blacks in radiation-curable adhesive systems.

Recommended levels

Amount of additive (as supplied) based on the pigment:

Titanium dioxide: 2.5-5 %
Organic pigments: 10-20 %
Carbon black: 10-20 %

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
info@byk.com
www.byk.com



Download
our app:
byk.com/app

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.