

## SCONA 20097

Coupling agent for filler and fiber-reinforced polypropylene composites to ensure super adhesion to the matrix. Compatibilizer for blends of polypropylene with polar polymers to improve mechanical and optical properties.

### Product data

#### Composition

Chemically modified polypropylene homopolymer

#### Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Grafting functionality: Maleic anhydride  
Grafting level: 0.40–0.50 % \*  
MFR (190 °C, 1.2 kg): 25–30 g/10 min \*\*  
Delivery form: Pellet  
Color: off-white

\* according to the BYK FTIR test method  
\*\* measured with a die 8/1

#### Storage and transportation

Store in sealed containers in a cool, dry, and well-ventilated location.

### Applications

#### Thermoplastics

##### Special features and benefits

SCONA 20097 is a polymeric modifier based on polypropylene homopolymer functionalized with a high degree of maleic anhydride. It has excellent wetting properties because of its very low viscosity. The additive is an excellent compatibilizer for blends of polypropylene and polar polymers such as polyamides and ethylene vinyl alcohol and improves the dispersion of the polymer polar material. This results in better mechanical and optical properties of the compatibilized material. It also acts as an excellent coupling agent for short and long glass fiber-reinforced polyolefins and improves their physical, mechanical, and thermal properties. In addition, SCONA 20097 can be used as a coupling agent in natural fiber-reinforced and wood fiber-reinforced composites as well as a dispersing aid for propylene/filler composites (e.g. aluminum hydroxide (ATH)). The additive has exceptional mechanical properties, a good price-performance ratio, a very weak odor, low VOC content and share of emissions.

## Recommended use

Compatibilizer	<input checked="" type="checkbox"/>
Coupling agent	<input checked="" type="checkbox"/>
Dispersing aid	<input type="checkbox"/>

especially recommended     recommended

## Recommended levels

Coupling agent: 1–4 % additive (as supplied) based upon the total formulation, depending on the fiber content.

Compatibilizer: 5–30 % additive (as supplied) based upon the polypropylene content in polymeric blends.

Dispersing aid: 1–4 % additive (as supplied) based upon the total formulation, depending on filler content. The above recommended levels can be used for orientation.

The optimum dosage should be determined by application-related test series.

## Incorporation and processing instructions

This product can be added via volumetric or gravimetric dosing units during processing in all types of extruders, blow, molding, and injection molding machines. In filled materials, to ensure good wetting of fibers/fillers, feeding through the main feed is preferred.



### BYK-Chemie GmbH

Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.