

BYK-3481

100 % silicone surfactant for aqueous systems to improve substrate wetting by means of a strongly reduced surface tension in the liquid coating. Excellent defoaming properties and anti-cratering effect combined with good leveling properties, particularly suitable for clearcoats.

Product data

Composition

Polyether-modified polydimethylsiloxane

SVHC label-free
(EU SDS)

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.02 g/ml
Active substance: 100 %
Flash point: > 85 °C

Storage and transportation

Store in a cool, dry, well-ventilated place.

Applications

Coatings industry

Special features and benefits

BYK-3481 combines various important properties in a single additive. In the first instance, it strongly reduces the static surface tension in the liquid coating, and therefore particularly improves the substrate wetting. Additionally, good leveling and an excellent defoaming effect are achieved, particularly with regard to the manufacturing of coatings and spray application. BYK-3481 is extremely suitable for critical substrates, e.g. plastics or contaminated metal surfaces. The product is even effective at a low dosage. It can also be post-added as an anti-cratering additive/troubleshooting additive, and incorporated at moderate shear rates. BYK-3481 requires a small proportion of organic cosolvents when it is used in aqueous systems. BYK-3481 is extremely compatible and particularly suitable for clearcoat systems.

Recommended use

General industrial coatings	<input checked="" type="checkbox"/>
Marine and protective coatings	<input checked="" type="checkbox"/>
Automotive coatings	<input type="checkbox"/>
Architectural coatings	<input type="checkbox"/>
Wood and furniture coatings	<input type="checkbox"/>
Floor coatings	<input type="checkbox"/>

especially recommended recommended

Recommended levels

0.05–0.5 % (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

BYK-3481 can be added to the letdown product or as a post-additive.

Special note

BYK-3481 is a silicone-containing surface additive. It is therefore recommended to check the intercoat adhesion and recoatability when it is used in multi-layer systems.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.