

BYK-MAX HS 4302

Granulated long-term thermal stabilizer for the use in PP-based glass mat thermoplastics (GMT) and long-fiber-reinforced PP products (LFT).

Product Data

Composition

Additive formulation

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density: 500-650 kg/m³
 Active substance: 30 %
 Supplied as: White to off-white granulate

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Store in a cool, dry and well-ventilated location.

Applications

Thermoplastics

Special Features and Benefits

BYK-MAX HS 4302 has a synergistic formulation of processing and thermal stabilizers, which protect polymers at high temperatures by decomposing reactive peroxides, and prevent the thermo-oxidative decomposition of the end product using radical scavengers. In addition, BYK-MAX HS 4302 has a very positive influence on long-term heat aging (LTHA), which makes it possible to comply with the automotive standard specifications more easily. The product does not affect the bonding properties and is non-migrating. BYK-MAX HS 4302 consists of a non-adhesive granulate, and is dust-free as well as being safe and easy to handle.

Recommended Use

Long fiber-reinforced pellets for automotive parts	■
Mounting supports	■
Bumpers	■
Structural components	■

■ especially recommended □ recommended

Recommended Levels

2-4 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added via volumetric or gravimetric dosing units during processing in all extruders and injection molding machines.

Special Note

The product is suitable for processing at temperatures up to 300 °C.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOÍSITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITÉ®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.