

BYK-S 732

常温硬化型エポキシおよびポリウレタン系樹脂用の湿潤性を備えた無溶剤型脱泡剤

製品データ

組成

ポリエーテル変性メチルアルキルポリシロキサンコポリマー

一般性状

本データシートに記載されている数値は代表値であり、品質規格ではございません。

密度 (20 °C): 0.93 g/ml
屈折率 (20 °C): 1.448
引火点: > 65 °C

食品接触用途

最新の食品接触に関する法的適合状況についてはお問い合わせ下さい。または、下記URLにてご確認下さい。
www.byk.com

適用分野

熱硬化型樹脂系

特長

この脱泡剤は、強化/フィラー含有の常温硬化型エポキシ樹脂およびポリウレタン樹脂における空気の混入と気孔の発生を抑制します。本添加剤は表面張力を低下させ、ガラス繊維、炭素繊維、シリカ砂などの補強材の濡れ性を向上させます。

推奨添加量

全配合に対して添加剤として、0.1–1 %

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

添加方法

この脱泡剤は、硬化剤を添加する前に、樹脂に均一に攪拌して添加してください。
フィラー含有システムでは、製造中に攪拌されて混入した空気を直ちに除去するため、フィラーよりも先にこの添加剤を添加することをお勧めします。



**Your local
contact**

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.