

## BYK-UV 3576

Crosslinkable surface additive for radiation curable systems for improving substrate wetting and leveling without foam stabilization.

### Product Data

#### Composition

Solution of a multi-acrylic functional, modified polydimethylsiloxane

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.07 g/ml  
 Refractive index: 1.462  
 Active substance: 40 %  
 Solvents: Tripropylene glycol diacrylate (TPGDA)  
 Flash point: > 60 °C

#### Storage and Transportation

To be stored and transported at a temperature between 0 °C and 40 °C. Protect the product from direct sunlight.

### Applications

#### Coatings Industry

#### Special Features and Benefits

BYK-UV 3576 displays a low to moderate reduction in surface tension and improves substrate wetting. The surface slip is not increased, or only slightly, and leveling is improved. The product does not cause foam to be stabilized; in some systems a defoaming effect is noticed. As a result of its multiple acrylic functionality BYK-UV 3576 crosslinks with radiation curable systems and thereby produces long-lasting effects without migrating. Its recoatability is good in most systems, however this must be checked. The product is very compatible and causes no haze in the coating system. BYK-UV 3576 is suitable for solvent-free, solvent-borne, and aqueous systems.

#### Recommended Use

Wood and furniture coatings	■
Industrial coatings	■

■ particularly recommended    □ recommended

## Recommended Levels

0.1-0.3 % additive (as supplied) based upon total formulation, in exceptional cases up to 1 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

## Overprint Varnishes

### Special Features and Benefits

BYK-UV 3576 improves substrate wetting and the leveling of 100%, UV-curing overprint varnishes. The good compatibility with standard binders enables highly transparent overprint varnishes to be produced.

### Recommended Use

Recommended for 100 % UV overprint varnishes.

## Recommended Levels

0.3-1 % additive (as supplied) based upon total formation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITÉ®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.