

## CLOISITE 116

### 製品データ

#### 組成

CLOISITE 116 は天然ベントナイトです。

#### 一般性状

本データシートに記載されております数値は代表値で、品質規格値ではございません。

水分:	8-13 %
代表的な乾燥粒子径:	<15 $\mu$ m ( $d_{50}$ )
色:	オフホワイト
かさ密度:	340g/l
比重:	2.8g/cm <sup>3</sup>
X 線結果:	$d_{001} = 1.25\text{nm}$

#### 推奨用途

CLOISITE 116をプラスチックおよびゴムに使用すると、補強性、CLTE、相乗的難燃性およびバリア性などの各種物理的性質が向上します。

### ビックケミー・ジャパン株式会社

本社: 東京都新宿区市谷本村町3-29

大阪: 大阪市北区堂島浜1-4-4

<http://www.byk.com/jp>

BYK-Chemie GmbH  
P.O. Box 10 02 45  
46463 Wesel  
Germany  
Tel: +49 281 670-0  
Fax: +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ACTAL®, ADJUST®, ADMETROL®, BENTOLITE®, CLAYTONE®, CLOISITE®, CORASIL®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SCP®, TIXOGEL®, Y25® are registered trademarks of BYK Additives.

ANTI-TERRAP®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKIET®, BYKORPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATON®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATON®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONAP® is a registered trademark of BYK Kometa.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany