

GELWHITE-H

High-purity rheology additive based on carefully selected natural bentonite, for use in personal care applications as a thixotropic gelling agent in aqueous systems with excellent anti-settling and stabilizing properties (COSMOS APPROVED, NATRUE Approved).



NATRUE Approved

Product data

Composition

Highly purified phyllosilicate
 (INCI: Bentonite or Montmorillonite)

Vegan

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density:	290-434 kg/m ³
pH value (2 % in water):	9.5-10.5
Water content:	5-8 %
Sieve residue (200 Mesh/74 µm):	0.0 %
Lead content:	< 40 mg/kg
Arsenic content:	< 5 mg/kg
Swelling:	min. 24 ml
Brightness:	min. 77
Color:	white
Delivery form:	powder

Storage and transportation

Product shelf life in unopened original packaging: 36 months

Store dry in sealed containers. To be stored and transported between -30 °C and 50 °C.

Applications

Personal care

Special features and benefits

GELWHITE-H is a highly purified bentonite obtained from selectively mined, extremely pure mineral deposits by means of a unique process providing unequalled high purity, whiteness, and brightness. The additive is purely inorganic and stable against diluted acids and bases. It is highly compatible with anionic and nonionic surfactants and can be used to thicken and stabilize oil-in-water emulsions. Gels produced with GELWHITE-H are resistant to oxidation and microbial degradation.

Recommended use

Creams and lotions	<input checked="" type="checkbox"/>
Sunscreen products	<input checked="" type="checkbox"/>
Antiperspirants/deos	<input checked="" type="checkbox"/>
Facial masks	<input checked="" type="checkbox"/>
Bath and shower gels	<input checked="" type="checkbox"/>
Liquid makeup	<input checked="" type="checkbox"/>
Blush	<input checked="" type="checkbox"/>
Eye makeup	<input checked="" type="checkbox"/>
Hair care products	<input checked="" type="checkbox"/>
Hair styling products	<input checked="" type="checkbox"/>

especially recommended recommended

Recommended levels

1-10 % additive (as supplied) based on the total formulation, depending on the application.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

GELWHITE-H is hydrophilic and can be easily wetted by water. For maximum efficiency, complete dispersion of the material is required. Warm water can be used to facilitate the dispersion. The additive is added as a powder to pure water while stirring slowly. The stirring speed is then increased (800–3000 rpm) and the powder is dispersed for 15 minutes. GELWHITE-H should be completely hydrated (recommended hydration time: 10 minutes) before all other components of the formulation are added to the dispersion. The additive can also be used as a prepared pre-gel (with 5–10% GELWHITE-H). To avoid post-thickening effects, this pre-gel should be allowed to age overnight. It is then slowly added to the water phase of the formulation while stirring at low speed.



Your local
contact

BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
info@byk.com
www.byk.com



Download
our app:
byk.com/app

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.