

# PURABYK-R 5501 XR

Rheology additive based on synthetic phyllosilicate for aqueous systems to provide thixotropic stabilization and to form shear-thinning hydrogels from aqueous solutions of hypochlorous acid (HClO). Gamma-irradiation-sterilized version of PURABYK-R 5501.

## Product data

### Composition

Synthetic (modified) phyllosilicate  
 (INCI: Sodium Magnesium Fluorosilicate (nano))

### Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density:	1000 kg/m <sup>3</sup>
pH value (2 % in water):	9.7
Water content:	< 10 %
Total viable count:	< 10 cfu/g
Delivery form:	powder

### Storage and transportation

Product shelf life in unopened original packaging: 48 months  
 Moisture sensitive. Store dry. To be stored and transported between 0 °C and 30 °C in the unopened original container.

## Applications

### Home care and I&I

#### Special features and benefits

Thanks to its inorganic structure, PURABYK-R 5501 XR offers good compatibility and excellent stability towards aqueous solutions of hypochlorous acid. Adding the additive leads to the formation of a gel structure. This enables a significantly longer contact time with the surface compared to water-thin solutions, which in turn improves the effectiveness of the disinfectant. Thanks to the resulting thixotropic flow behavior, the gel is easy to apply and can also be applied by spraying. PURABYK-R 5501 XR is very well suited for applications in the skin-friendly pH range of 5.5–6.5, in which the hypochlorous acid exhibits optimal antimicrobial activity as well as maximum stability.

#### Recommended use

Hydrogels (for disinfection)	<input checked="" type="checkbox"/>
------------------------------	-------------------------------------

especially recommended  recommended

**Recommended levels**

2-5 % additive (as supplied) based on the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

**Incorporation and processing instructions**

PURABYK-R 5501 XR must be pre-mixed with ultrapure water before the HClO solution is added. The additive is added to the ultrapure water gradually over a period of 10 to 20 seconds (at 20 °C ± 5 °C) while stirring quickly. It should be stirred fast enough that a turbulent vortex current is formed, so that the powder is well dispersed and clumps are avoided. After addition is complete, stirring is continued for 20 minutes. Avoid introducing air by stirring at the correct speed and by ensuring the stirrer is in the optimal position. When completely dispersed, a clear, colorless, and low-viscosity pre-mix is obtained. The hypochlorous acid solution and other components of the formulation can now be added while stirring. The pH adjustment should be done at the end.

The time required to form the gel structure depends on the salt content of the solution and the amount of additive added.

**Special note**

PURABYK-R 5501 XR is not compatible with cationic compounds. For pH adjustment, a buffer solution of sodium dihydrogen phosphate or ortho-phosphorous acid is suitable. As the additive is a weak base and can thus lead to an increase in pH, it may be necessary to adjust the initial pH to a value below the target pH value. The addition of ortho-phosphorous acid results in a rapid and very significant increase in viscosity. For easier dosing, a 10% solution of the acid can alternatively be added.

**Personal care****Special features and benefits**

Thanks to its inorganic structure, PURABYK-R 5501 XR offers good compatibility and excellent stability towards aqueous solutions of hypochlorous acid. Adding the additive leads to the formation of a gel structure. This enables a significantly longer contact time with the skin and improved effectiveness compared to water-thin formulations. Thanks to the resulting thixotropic flow behavior, the gel is easy to apply and can also be applied by spraying. PURABYK-R 5501 XR is very well suited for applications in the skin-friendly pH range of 5.5–6.5, in which the hypochlorous acid exhibits optimal antimicrobial activity as well as maximum stability.

**Recommended use**

Hydrogels (with hypochlorous acid)	<input checked="" type="checkbox"/>
------------------------------------	-------------------------------------

especially recommended    recommended

**Recommended levels**

2-5 % additive (as supplied) based on the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

**Incorporation and processing instructions**

PURABYK-R 5501 XR must be pre-mixed with ultrapure water before the HClO solution is added. The additive is added to the ultrapure water gradually over a period of 10 to 20 seconds (at 20 °C ± 5 °C) while stirring quickly. It should be stirred fast enough that a turbulent vortex current is formed, so that the powder is well

dispersed and clumps are avoided. After addition is complete, stirring is continued for 20 minutes. Avoid introducing air by stirring at the correct speed and by ensuring the stirrer is in the optimal position. When completely dispersed, a clear, colorless, and low-viscosity pre-mix is obtained. The hypochlorous acid solution and other components of the formulation can now be added while stirring. The pH adjustment should be done at the end.

The time required to form the gel structure depends on the salt content of the solution and the amount of additive added.

### Special note

PURABYK-R 5501 XR is not compatible with cationic compounds. For pH adjustment, a buffer solution of sodium dihydrogen phosphate or ortho-phosphorous acid is suitable. As the additive is a weak base and can thus lead to an increase in pH, it may be necessary to adjust the initial pH to a value below the target pH value. The addition of ortho-phosphorous acid results in a rapid and very significant increase in viscosity. For easier dosing, a 10 % solution of the acid can alternatively be added.



Your local  
contact

#### BYK-Chemie GmbH

Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)



Download  
our app:  
[byk.com/app](http://byk.com/app)

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYK®, RECYCLOBYK®, RHEOBYK®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.