

# VISCOBYK-5125

Low volatile viscosity depressant for PVC plastisols. All-purpose.

## Product data

### Composition

Blend of carboxylic acid esters and wetting and dispersing components

### Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.87 g/ml
Solidification point:	< -7 °C
Flash point:	> 140 °C
Refractive index (20 °C):	1.460

### Storage and transportation

Separation or turbidity may occur at temperatures below -5 °C.  
Warm to 20 °C and mix well.

## Applications

### PVC plastisols

#### Special features and benefits

The additive reduces the viscosity in PVC plastisols and is recommended for universal use in all systems.

#### Recommended levels

1–7.5 % additive (as supplied) based on the PVC resin, in exceptional cases up to 10 %.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

#### Incorporation and processing instructions

The additive may be added during the plastisol manufacturing process or shortly prior to processing.



Your local  
contact

**BYK-Chemie GmbH**  
Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

info@byk.com  
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFLOUR®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.