

## Starting point formulation – Pigment concentrates for solvent-free UV systems with DISPERBYK-2013

<b>Pigment</b>	<b>Kronos 2310</b>	<b>Bayferrox 130M</b>	<b>Irgazin Red L3660 HD</b>	<b>Hostaperm Yellow H4G</b>	<b>Heliogen Blue L6875F</b>	<b>Heliogen Green L8730</b>	<b>Special Black 100</b>
<b>Supplier</b>	Tronox	Lanxess	Sun Chemical	Sudarshan	Sun Chemical	Sun Chemical	Orion Engineered Carbons

Position	Component	Supplier	Function	PW 6	PR 101	PR 254	PY 151	PB 15:2	PG 7	PB 7
1	DPGDA*	BASF	Monomer	22.50	31.80	54.00	47.50	70.90	68.50	50.50
2	BYK-1788	BYK	Defoamer	0.50	0.50	0.50	0.50	0.50	0.50	0.50
3	RHEOBYK-7410 ET	BYK	Rheology	0.50	0.50	-	-	-	-	-
4	DISPERBYK-2013	BYK	Wetting and dispersing	1.50	7.20	10.50	12.00	6.60	8.00	14.00
5	Pigment	See headline	Color	75.00	60.00	35.00	40.00	22.00	23.00	35.00
<b>Total</b>				<b>100.00</b>						

### Instructions

Premix position 1–4, add pigment and add 1:1 glass beads (1.3 mm) and disperse (grinding) well.

### Characteristic data

Additive dosage (solids on pigment)

DISPERBYK-2013	2.00%	12.00%	30.00%	30.00%	30.00%	35.00%	40.00%
----------------	-------	--------	--------	--------	--------	--------	--------

### Grinding process:

Pigment	Time (min)	Speed RPM	Temperature
TiO <sub>2</sub> :	30 min	8,000 rpm	40 °C
Iron oxide red:	30 min	8,000 rpm	40 °C
Org. pigments:	40 min	10,000 rpm	40 °C
Carbon black:	60 min	10,000 rpm	40 °C

\* DPGDA: Dipropylene glycol diacrylate



Your local  
contact

**BYK-Chemie GmbH**  
Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, NANOBYPK®, OPTIBENT®, OPTIGEL®, PURABYPK®, RECYCLOBYPK®, RHEOBYPK®, SCONA®, SILBYPK®, TIXOGEL® and VISCOBYPK® are registered trademarks of the BYK group.

The information contained herein is based on our current knowledge and experience. No warranties, guarantees and/or assurances of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. Any information about suitability, use or application of the products is non-binding and does not constitute a commitment regarding the products' properties, use or application. Contractual terms and conditions, in particular agreed product specifications, always take precedence. We recommend that you test our products in preliminary trials to determine their suitability for your intended purpose prior to use. We reserve the right to make any changes and to update the information herein without notice.

Download  
our app:  
[byk.com/app](http://byk.com/app)

