

# BYK-P 4100

Processing additive for filled, thermoplastic compounds as well as for PVC plastisols and PVC calender applications.

## Product Data

### Composition

Copolymer with acidic groups

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 14 mg KOH/g

Density (20 °C): 0.99 g/ml

## Applications

### Thermoplastics

#### Special Features and Benefits

BYK-P 4100 is a surface-active processing additive for use in filled, thermoplastic compounds. During compounding, the additive reduces the required torque. The output capacity and the melt volume rate (MVR) are increased. The tensile strength, E-modulus and notch impact strength are increased in the finished part. The printability is improved.

#### Recommended Use

Mineral fillers	<input checked="" type="checkbox"/>
Flame retardants	<input checked="" type="checkbox"/>
Wood plastic composites (WPC)	<input checked="" type="checkbox"/>
Glass fibers HMC	<input type="checkbox"/>

especially recommended     recommended

#### Recommended Levels

0.25-2% additive (as supplied) based upon the filler.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

Ideally, the additive is added at the same time as the liquids, and then the solids are incorporated. Post addition is also possible.

## PVC applications

### Special Features and Benefits

BYK-P 4100 is a surface-active processing additive for use in PVC plastisols and PVC calender applications.

#### PVC plastisols:

In PVC plastisols, the additive has very good release properties from gelling drums, release papers, flat screens and molds.

It also influences the cell structure of chemically blown foams and improves the resilience and increases the air permeability.

Only specific PVC types are suitable for open cell foams. An open cell structure can only be achieved if the formulation components and process parameters are coordinated to one another. The use of BYK-P 4100 can bring about an increased water uptake.

#### PVC calender applications:

In PVC calendar applications, the additive has very good release properties during the processing of soft, semi-rigid and rigid PVCs. The printability of the end product is also improved.

### Recommended Levels

0.1-3 % additive (as supplied) based on the total formulation, depending on the desired effect.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

Ideally, the additive is added at the same time as the liquids, and then the solids are incorporated. Post addition is also possible.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITÉ®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.