

CLAYTONE-ER

High efficiency rheological additive suitable for use in mineral oil and synthetic base fluids to increase the carrying capacity and hole cleaning capabilities. The product is also an effective suspension agent for polymer slurries.

Product Data

Composition

Alkyl quaternary ammonium bentonite

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Sieve passing (325 Mesh/44 µm):	80 %
Specific Gravity:	1.6
Loss on ignition (1 h, 1000 °C):	41.5 %
Bulk density:	22 lb/ft ³ /352 kg/m ³
Supplied as:	Free-flowing powder

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Moisture sensitive. Pallet stacking should be no more than two pallets high in order to prevent compaction.

Applications

Oil-Based Drilling Fluids

Special Features and Benefits

- Minimal shear required
- Improves sag resistance
- High YP/PV ratio
- Wet processed, highly purified
- Secondary benefits include: filtration control and emulsion stability

Recommended Uses

CLAYTONE-ER is recommended for drilling fluids utilizing mineral oil or synthetic fluids as the base oil and where the bottom hole temperatures will not exceed 350 °F (175 °C). This product is well suited for mud plants with minimal mixing shear capabilities.

CLAYTONE-ER is useful as a suspension agent for concentrated polymer slurries, such as xanthan or guar gum.

Example formulation #1: 10.5 pounds/gallon 70/30 Internal Olefin C16-C18

	350 ml formulation	Multi-mixer at 11,000 rpm
Amodrill* 1000	207 ml	
CLAYTONE-ER	8 g	Mix 5 min.
Lime	3 g	Mix 5 min.
Emulsifier Package	10 g	Mix 5 min.
CaCl ₂ (25 % in water)	97 ml	Mix 20 min.
Barite	120 g	Mix 5 min.

* Amodrill 1000 is a product of Ineos
Silverson mixer at 6,000 rpm for 5 minutes after mixing.

figure 1

Lab results

Properties (at 150 °F)	Initial	After Hot Rolling	
		16 h at 150 °F	16 h at 250 °F
Rheological properties			
600 rpm reading	70	69	59
300 rpm reading	51	47	38
200 rpm reading	43	37	30
100 rpm reading	33	27	22
6 rpm reading	17	13	10
3 rpm reading	16	11	9
Plastic Viscosity (cP)	19	22	19
Yield Point (lb/100 ft ²)	32	25	19
Electrical Stability	870	417	172

figure 2

Example formulation #2: 10.7 pounds/gallon 67/33 Mineral Oil

	350 ml formulation	Multimixer mit 11.000 U/min
Destillat 822*	199 ml	
CLAYTONE-ER	2.3 g	Mix 5 min.
Lime	3 g	Mix 5 min.
Emulsifier Package	10 g	Mix 5 min.
CaCl ₂ (25 % in water)	97 ml	Mix 20 min.
Barite	130 g	Mix 5 min.

* Distillate 822 is a product of Gibson's Energy
Silverson mixer at 6,000 rpm for 5 minutes after mixing.

figure 3

Lab results

Properties (at 150 °F)	Initial	After Hot Rolling	
		16 h at 150 °F	16 h at 250 °F
Rheological properties			
600 rpm reading	56	56	53
300 rpm reading	35	39	35
200 rpm reading	25	31	25
100 rpm reading	18	23	18
6 rpm reading	6	10	8
3 rpm reading	5	9	7
Plastic Viscosity (cP)	21	17	18
Yield Point (lb/100 ft ²)	14	22	17
Electrical Stability	832	709	540

figure 4

Recommended Levels

A 2-8 lb/barrel (6-23 kg/m³) addition is typically used for most conventional oil-based invert drilling fluids. Actual CLAYTONE-ER usage will depend on the base oil, oil/water ratio, solids, and the emulsifier package.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

CLAYTONE-ER requires low to moderate shear and temperature to fully yield. Full yield is typically achieved through one bit pass. A small stream of water can be used to reduce yield time. (The water phase of invert emulsions provides the polar activation).



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany