

RHEOBYK-T 1010 VF

VOC-free associative thickener (HEUR) for aqueous systems to generate Newtonian flow behavior.

Product Data

Composition

Solution of a polyurethane

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Active substance: 22.5 %
Density (20 °C): 1.04 g/ml
Solvents: Water
pH value: 8

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Transport and store in a dry place, in an unopened original container, at temperatures between 5 °C and 35 °C.

VOC-free (< 1500 ppm)
APEO-free
Tin-free

Applications

Coatings Industry

Special Features and Benefits

RHEOBYK-T 1010 VF increases the viscosity in the high-shear range with an extremely low impact in the low-shear range. It improves processability, leveling, and storage stability. It reduces spattering during application. In addition, greater layer thicknesses can be achieved along with an excellent balance between the flow properties and leveling. The additive is liquid and therefore easy to handle and is VOC-, APEO-, and tin-free. It is not necessary to adjust the pH value or control the temperature during incorporation. RHEOBYK-T 1010 VF has no negative effect on gloss, color acceptance or rub-out.

Recommended Use

RHEOBYK-T 1010 VF is preferably used in emulsion paints and coatings that are based on acrylics, styrene acrylics and vinyl acetate copolymer binders as well as PU and alkyd emulsions. It is also well suited for aqueous wood and furniture coatings based on PU, acrylics and UV-curing systems.

Architectural coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input type="checkbox"/>
General industrial coatings	<input checked="" type="checkbox"/>

especially recommended recommended

Recommended Levels

1.0-4.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Addition under stirring ensures optimum distribution and the best possible effectiveness and reproducibility in applications. RHEOBYK-T 1010 VF is suitable for adding to the mill-base, to the letdown, or as a post additive to retroactively adjust the rheological properties.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSORB®, RECYCLOSTAB®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany