

SCONA 25097

Coupling agent for filler and fiber-reinforced polypropylene composites to ensure super adhesion to the matrix. Compatibilizer for blends of polypropylene with polar polymers to improve mechanical and optical properties.

Product data

Composition

Chemically modified polypropylene copolymer

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Grafting functionality: Maleic anhydride
Grafting level: 0.58–0.63 %*
MFR (190 °C, 1.2 kg): 20–30 g/10 min**
Delivery form: Pellet
Color: off-white

* according to the BYK FTIR test method
** measured with a die 8/1

Storage and transportation

Store in sealed containers in a cool, dry, and well-ventilated location.

Applications

Thermoplastics

Special features and benefits

SCONA 25097 is a polymeric modifier based on polypropylene copolymer functionalized with a high degree of maleic anhydride. It has excellent wetting properties because of its very low viscosity. The additive is an excellent compatibilizer for blends of polypropylene and polar polymers such as polyamides and ethylene vinyl alcohol and improves the dispersion of the polymer polar material. This results in better mechanical and optical properties of the compatibilized material. In addition, it is an excellent coupling agent for short and long glass fiber-reinforced polyolefins and improves their physical, mechanical, and thermal properties. SCONA 25097 also acts as a coupling agent in natural fiber-reinforced and wood fiber-reinforced composites as well as a dispersing aid for polypropylene/filler composites (e.g. aluminium hydroxide (ATH)). SCONA 25097 has exceptional mechanical properties, a good price-performance ratio, a very weak odor, if any, as well as low VOC content and emissions.

Recommended use

Compatibilizer	<input checked="" type="checkbox"/>
Coupling agent	<input checked="" type="checkbox"/>
Dispersing aid	<input type="checkbox"/>

especially recommended recommended

Recommended levels

Coupling agent: 1–4 % additive (as supplied) based upon the total formulation, depending on the fiber content.

Compatibilizer: 5–30 % additive (as supplied) based upon the polypropylene content in polymeric blends.

Dispersing aid: 1–4 % additive (as supplied) based upon the total formulation, depending on filler content.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

This product can be added via volumetric or gravimetric dosing units during processing in all types of extruders, blow molding, and injection molding machines. In filled materials, to ensure good wetting of fibers/fillers, feeding through the main feed is preferred.



BYK-Chemie GmbH

Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.