

SCONA TPPP 8112 FA

TPE-Sオーバーモルディングコンパウンド用密着性付与剤、天然繊維コンパウンドおよびポリプロピレンのワンパック化に適したカップリング剤

製品データ

組成

マレイン酸無水物で高機能化させたポリプロピレン

一般性状

本データシートに記載されております数値は代表値であり、品質規格ではございません。

MFR (190 °C, 2.16 kg): > 80 g/10 分

揮発分 (3 h, 110 °C): < 0.5 %

MAH含有量: 1.4 %

形状: 粉末

食品接触用途

最新の食品接触用途に関する法的適合状況についてはお問い合わせ下さい。または、www.byk.comにてご確認下さい。

貯蔵および輸送

35°C以下の温度、相対湿度80%未満で保管して下さい。直射日光および水との接触を避けて下さい。

特記事項

本添加剤の粒状バージョンがSCONA TPPP 8112 GAになります。

適用分野

熱可塑性樹脂

特長

TPE-Sオーバーモルディングコンパウンドに使用すると、(PC, PA, ABSなどの)硬質基材への密着性が向上します。グラフト化レベルが高いため、TPEコンパウンド中のPPの一部を本添加剤で置き換えて下さい。PP天然繊維コンパウンドに使用すると、機械的性質が大幅に向上し、吸水量が低下します。本添加剤は粉末なので、ワンパック化およびマスターバッチの製造に最適です。

推奨添加量

ファイバーコンパウンド中の天然繊維およびオーバーモールドイングコンパウンド中のPP含有量により、全配合に対して添加剤として0.8-3%

上述の推奨添加量は初期値としてご利用下さい。最適添加量は実際に試験を行い、決定して下さい。

添加方法

本添加剤はコンパウンド中に均一に分散させて下さい。TPE接着剤には、粒状の密着性付与剤(SCONA TPPP 8112 GA)を使用して下さい。

ビックケミー・ジャパン株式会社

本社: 東京都新宿区市谷本村町3-29

大阪: 大阪市北区堂島浜1-4-4

<http://www.byk.com/jp>



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany