

BYK additives for asphaltite suspensions


Additive package for 38 % asphaltite suspensions for water-based and oil-based fluids

A combination of BYK rheology and wetting and dispersing additives creates a stable suspension of asphaltite. The slurry is easily and readily dispersible in both water-based and oil-based fluids. The formulated slurry is additionally shear thinning for ease of use and handling.

Formulations

Component	Formulation for untreated asphaltite (weight %)	Formulation for treated asphaltite (weight %)
Water	41.45	41.65
Butoxytriglycol	20.00	20.00
LAPONITE-EP	0.35	0.35
DISPERBYK-192	0.10	-
DISPERBYK-2013	0.10	-
Asphaltite	38.00	38.00

Preparation of asphaltite suspension



Add water and butoxytriglycol.

Mix with small vortex.



Mix in LAPONITE-EP while stirring.



Mix in DISPERBYK-192 and DISPERBYK-2013 for untreated asphaltite formula.



Add asphaltite.




Increase speed to 2500 rpm. Mix for 20 minutes.



Stable suspension.

Stable asphaltite suspension for easy use in oil- and water-based fluids







Readily and easily dispersible in oil-based fluids



Readily and easily dispersible in water-based fluids

For additional technical information on LAPONITE rheology additives, and DISPERBYK wetting and dispersing additives please refer to www.byk.com.

BYK-Chemie GmbH P.O. Box 10 02 45 46462 Wesel Germany Tel +49 281 670-0 Fax +49 281 65735

info@byk.com www.byk.com ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKETOL®, BYKDET®, BYKOZBLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERAFAK®, CERAFLOUR®, CERAFIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, FULCAT®, GRAMMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIFLO®, OPTIFLO®, OPTIFLO®, OPTIFLO®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25° are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.



